



The mechanism of fracture for entangled polymer liquids in extensional flow

Huang, Qian; Yu, Liyun; Wingstrand, Sara Lindeblad; Skov, Anne Ladegaard; Hassager, Ole

Publication date:
2017

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):
Huang, Q., Yu, L., Wingstrand, S. L., Skov, A. L., & Hassager, O. (2017). *The mechanism of fracture for entangled polymer liquids in extensional flow*. Abstract from 89th Annual Meeting of the Society of Rheology, Denver, Colorado, United States.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

The Society of Rheology 89th Annual Meeting

October 8-12, 2017 - Denver, Colorado

Paper Number

SM20

[+ \(mp/AddToMyProgram.aspx?ID=113&url=https%3a%2f%2fwww.rheology.org%2fsor17a%2fViewPaper%3fID%3d113\)](#) My Program

Session

Polymer Solutions and Melts

Title

The mechanism of fracture for entangled polymer liquids in extensional flow

Presentation Date and Time

October 10, 2017 (Tuesday) 1:55

Track / Room

Track 2 / Crystal B

Authors

(Click on name to view author profile)

1. Huang, Qian ([ViewAuthorProfile.aspx?ID=305](#)) (*Technical University of Denmark, Department of Chemical and Biochemical Engineering*)
2. Yu, Liyun ([ViewAuthorProfile.aspx?ID=306](#)) (*Technical University of Denmark*)
3. Wingstrand, Sara L. ([ViewAuthorProfile.aspx?ID=307](#)) (*Technical University of Denmark, Department of Chemical and Biochemical Engineering*)
4. Skov, Anne L. ([ViewAuthorProfile.aspx?ID=308](#)) (*Technical University of Denmark, Department of Chemical and Biochemical Engineering*)
5. Hassager, Ole ([ViewAuthorProfile.aspx?ID=15](#)) (*Technical University of Denmark, Department of Chemical and Biochemical Engineering*)

Author and Affiliation Lines

(in printed abstract book)

[Qian Huang](#), Liyun Yu, Sara L. Wingstrand, Anne L. Skov, and Ole Hassager

Department of Chemical and Biochemical Engineering, Technical University of Denmark, Kgs. Lyngby 2800, Denmark

Speaker / Presenter

Huang, Qian

Text of Abstract

In extensional flow of entangled polymer liquids, fracture may happen when the stretch rate is fast enough. High-speed imaging shows that the local shear rates near the crack tip can be 3 orders of magnitude higher than the stretch rate imposed. Such high shear rates correspond to the frequencies close to the third crossover point (in the glassy region) in linear viscoelastic (LVE) measurements [1]. This observation suggests that fracture happens in a much shorter length scale than entanglement strands, and thus the number of entanglements per chain (Z) may be an unimportant parameter in fracture.

In this work we investigate two groups of entangled polymer liquids. In Group I we compare polystyrene (PS) melts with poly(methyl methacrylate) (PMMA) solutions. The samples have the same number of Kuhn segments (N_e) per entanglement strand. We also compare PS solutions at a same concentration (so that N_e is the same) but with different solvents in this group. In Group II we compare PS solutions at different concentrations but with the same Z .

We first perform LVE measurements up to the frequency at the third crossover point. It has been experimentally confirmed that the distance between the first and second crossover points is related to Z for both melts and solutions [2]. We here show that the distance between the second and third crossover points is related to N_e for the entangled systems. We then stretch the samples in uniaxial extensional flow. We show that the critical strain at fracture decreases with increasing stretch rate, and reaches a constant value at faster rates. The value of the constant critical strain seems to be related to the maximum stretch ratio of the polymer chain (determined by N_e), while it is independent of Z . The results are also compared with the critical strain of chemically crosslinked polymer networks.

[1] Huang et al., PRL 117, 087801 (2016)

[2] Huang et al., Macromolecules 46, 5026-5035 (2013)